

SelectionLabel	'Source file'	Fe	V	Cr	Mn	Co	Ni	Cu	Zn	Ga	Ge	As	Se	Mo	Ag	Cd	In	Sn	Sb	Te	Ba	W	Au	Hg	Tl	Pb	Bi
Output_1_1	0035MPL.d	464000	0.029	0.1	0.14	4.12	1519	37	6.6	0.024	15.78	0.75	12.5	0.025	0.313	1.17	0.0047	0.081	6.5	0.49	0.22	0.0103	0.021	0.55	0.0095	70	1.85
Output_1_2	0045MPL.d	463000	0.024	0.33	0.36	4.58	2118	78	5.53	0.045	15.42	0.48	12	0	0.17	1.29	0.0104	0.078	2.63	0.08	0.081	0.0046	0.0148	0.4	0.005	6.7	0.166
Output_1_3	0055MPL.d	460000	0.027	0.21	2.33	2.69	5640	6.2	6.4	0.108	15.49	0.38	13.1	0.0063	0.024	0.01	0.0119	0.076	0.239	0.89	0.027	0.012	0.001	0.46	0.00275	0.66	0.115
Output_1_4	0065MPL.d	461000	0.016	0.27	0.18	2.17	4445	4	3.25	0.008	15.35	0.4	18.8	0.028	0.032	0.013	0.0036	0.01	0.46	0.57	0.375	0.008	0.0117	0.39	0.0021	1.72	0.094
Output_1_5	0075MPL.d	460000	0.019	0.09	0.19	1.97	5376	10.6	4.4	0.041	15.08	0.27	13.4	0.0027	0.036	0.0165	0.0072	0.067	0.199	1.03	0.029	0.0016	0.0059	0.62	0.0015	9.8	0.164
Output_1_6	0085MPL.d	459000	0.024	0.09	0.18	2.91	1087	36.9	1580	0.73	15.21	2.03	16.4	0.0245	5.32	4.63	0.228	0.156	3.33	1.38	0.21	0	0.038	1.07	0.00355	2830	15
Output_1_7	0095MPL.d	464000	0.029	0.05	0.02	3.81	1102	77	96	0.119	14.8	1.4	13.3	0.11	0.067	0.22	0.0185	0.081	0.212	0.22	0.083	0.0125	0.0102	0.47	0.0011	6.3	0.199
Output_1_8	0105MPL.d	461000	0.017	0.19	0.15	3.11	3737	33.8	24.9	0.97	15.1	0.4	15.6	0	0.074	0.065	0.0115	0.392	0.205	0.44	0.037	0.0065	0.0147	0.44	0.0027	13	0.209
Output_1_9	0115MPL.d	463000	0.013	0.24	0.17	5.98	2300	69	3.71	0.016	15.09	0.18	12	0	0.1	0.135	0.0044	0.067	1.68	0.33	0.18	0.009	0.0058	0.75	0.0016	7.1	0.462
Output_1_10	0125MPL.d	441000	0.027	0.14	0.03	9.72	6790	116	2700	0.16	14.7	3.98	24.7	0.0105	23.1	7.9	0.082	0.21	7.23	13.2	0.12	0.0085	0.098	2.76	0.0106	11940	60.5
Output_1_11	0135MPL.d	464000	0.01	0.27	0.21	9.82	1745	36.1	20.6	0.009	14.99	0.52	13	0	0.458	7.3	0.0059	0.051	5.89	0.46	0.275	0.0255	0.028	0.94	0.0061	26	1.21
Output_1_12	0145MPL.d	465000	0.027	0.35	0.05	3.25	684	1.42	3.84	0.016	15.26	0.33	11.3	0.0037	0.022	0.065	0.004	0.053	0.121	0.305	0.22	0.0017	0.0023	0.77	0.0005	0.623	0.088
Output_1_13	0155MPL.d	457000	0.019	0.27	0.09	0.532	7950	1.21	4.02	1.52	14.86	0.23	14.8	0.011	0.0015	0	0.00435	0.4	0.042	1	0.029	0	0.012	0.62	0.006	0.079	0.0134
Output_1_14	0165MPL.d	461000	0.027	0.35	0.09	4.69	3980	45	29.6	0.219	14.7	4.71	14.2	0.028	2.25	3.66	0.23	4.4	3.47	2.32	0.17	0	0.022	0.63	0.0039	34	4.03
Output_1_15	0175MPL.d	462000	0.011	0.22	0.12	0.805	2140	13.2	117	0.067	14.63	4.81	14.8	0.025	0.666	0.95	0.049	0.71	5.73	0.28	0.26	0.0037	0.041	0.57	0.0029	46.9	3

min	441000.00	0.01	0.05	0.02	0.53	684.00	1.21	3.25	0.01	14.63	0.18	11.30	0.00	0.00	0.00	0.01	0.04	0.08	0.03	0.00	0.00	0.39	0.00	0.08	0.01	
max	465000.00	0.03	0.35	2.33	9.82	7950.00	116.00	2700.00	1.52	15.78	4.81	24.70	0.11	23.10	7.90	0.23	4.40	7.23	13.20	0.38	0.03	0.10	2.76	0.01	11940.00	60.50
ср. сод	460333.33	0.02	0.21	0.29	4.01	3374.20	37.70	307.06	0.27	15.10	1.39	14.66	0.02	2.18	1.83	0.05	0.46	2.52	1.53	0.15	0.01	0.02	0.76	0.00	999.53	5.81
медіан	461000.00	0.02	0.22	0.15	3.25	2300.00	36.10	6.60	0.07	15.09	0.48	13.40	0.01	0.10	0.22	0.01	0.08	1.68	0.49	0.17	0.01	0.01	0.62	0.00	9.80	0.21
ст. откл	5777.63	0.01	0.10	0.57	2.74	2257.92	34.29	774.47	0.45	0.33	1.69	3.39	0.03	5.96	2.73	0.08	1.11	2.65	3.28	0.11	0.01	0.02	0.59	0.00	3112.14	15.61

	Co	Ni	Cu	Zn	As	Se	Ag	Cd	Sb	Te	Au	Hg	Pb	Bi
Co	1.00													
Ni	-0.10	1.00												
Cu	0.70	-0.09	1.00											
Zn	0.45	0.21	0.57	1.00										
As	0.13	0.03	0.31	0.46	1.00									
Se	0.28	0.51	0.37	0.81	0.45	1.00								
Ag	0.56	0.35	0.63	0.94	0.51	0.84	1.00							
Cd	0.79	0.01	0.51	0.70	0.47	0.52	0.70	1.00						
Sb	0.57	-0.16	0.45	0.49	0.59	0.35	0.54	0.74	1.00					
Te	0.55	0.47	0.60	0.87	0.49	0.84	0.98	0.65	0.49	1.00				
Au	0.53	0.21	0.58	0.88	0.67	0.81	0.92	0.78	0.76	0.87	1.00			
Hg	0.65	0.29	0.59	0.91	0.43	0.75	0.97	0.76	0.56	0.94	0.89	1.00		
Pb	0.54	0.35	0.62	0.95	0.45	0.84	1.00	0.68	0.51	0.97	0.91	0.97	1.00	
Bi	0.55	0.33	0.63	0.95	0.50	0.84	1.00	0.70	0.55	0.97	0.93	0.97	1.00	1.00